



VDX Dry Lubricant Spray

Product Information

Aerosol packaged VDX Dry Lubricant Spray is a medical-grade Polytetrafluoroethylene (PTFE) micro dispersion lubricant. This spray-applied lubricant dispenses in a precise spray pattern ideal for spotlubrication of springs, hinges, and mechanical pinch points in medical device assemblies. VDX provides a low cost, non-migrating inert coating that imparts ultra-low friction surfaces and eliminates sticking problems common in low-speed, light-load mechanical assemblies.

VDX Dry Lubricant Spray is a PTFE surface treatment. It offers many important benefits:

- High-performance PTFE lubricant; will not attract dust or dirt
- Factory calibrated PTFE content for consistent results
- · Fast drying with minimal odor
- Nonflammable; maximum safety in storage and use
- Oil free; non-migrating/non-staining; does not contain silicone
- Excellent for high temperature applications up to 500 °F (260 °C)
- Hostile to bioburden issues
- · Excellent materials compatibility; plastic-safe
- Compatible with ETO and radiation sterilization processes
- · Low cost; convenient aerosol dispensing
- · No special equipment requirements
- Imparts a low coefficient of friction of 0.06
- · ISO 10993* tested and certified

Physical & Chemical Properties	
Odor	Slight Ethereal
Solubility in Water	Not Soluble
% Volatile by Weight (Carrier)	100
Lubricant Coefficient of Friction	0.06
PTFE Particle Size Average Bulk Average Mean	1-15 (microns) 3.7 (microns)
Carrier Evaporation Rate (Ether = 1)	>1
Flash Point	Not Flammable
ISO 10993* Tested and Certified	Yes

* Contact MicroCare Medical for specifics regarding ISO 10993 certification.

Packaging	
Aerosol ¹ - 12 oz / 340 g	MCC-VDX
Aerosol Packaging	12 cans / box
Shelf Life	Unlimited
Recycle	

Note: Products sold by weight, not volume.

One-gallon and smaller sample containers are available upon request.

Application Methods

Formulated specially for medical device assembly and component uses, the aerosol packaged VDX Dry Lubricant is ready-to-use and calibrated with a concentration of PTFE optimized for most lubrication needs. Normal precautions (safety glasses, etc.) should be used when using this product. See product SDS prior to use for full details on health and safety. Treated surfaces should be clean and dry prior to application of the lubricant. To ensure the lubricant dispenses uniformly when sprayed, shake the can aggressively prior to each use. Hold the can 2 - 3 inches (5 - 8 cm) from the surface to be treated. For best results, apply a thin mist. The coating dries in seconds and can be seen on the part as a wax-like coating. A single treatment is adequate for most applications.

Contact *MicroCare* for details on alternative application methods including manual and automated liquid dipping, wiping, brushing or spraying.

Heat Treatment

Coated parts can be heat treated for greater coating durability. Heat-treatment offers enhanced durability by melting the coating onto the substrate of the part. The process is simple and involves heating the part surface to 300-315 °C (575-600 °F). Measure the surface temperature directly with a thermocouple. The coating appearance may change from opaque white to a darker translucent surface and finally appear clear wet. Maintain the surface temperature of the coated part (not the temperature of the ambient air) at recommended temperature for 5 - 10 minutes. If a white residue remains, buff with a soft cloth after cooling. No further treatment is required.

Environmental

VDX Dry Lubricant Spray formula is accepted by the U.S. Environmental Protection Agency (EPA) under the Significant New Alternatives Policy (SNAP) Program. Contact *MicroCare* for details related to EU REACH compliance requirements.

MicroCare.com

MicroCare, LLC

595 John Downey Drive New Britain, CT 06051 USA CAGE: OATV9 Tel: +1 860 827 0626 Toll Free: 1 800 638 0125 Email: TechSupport@MicroCare.com

MicroCare Europe BVBA

Vekestraat 29 B11 Industriezone 't Sas 1910 Kampenhout, Belgium Tel: +32 2 251 95 05 Email: EuroSales@MicroCare.com

MicroCare U.K. Ltd Seven Hills Business Centre South Street, Morley Leeds, United Kingdom LS27 8AT Tel: +44 (0) 113 3609019 Email: mcceurope@microcare.com

in D F Y Follow Us!

MicroCare Asia Pte Ltd

102E, Pasir Panjang Road Citilink, #05-06 Singapore 118529 Tel: +65 6271 0182 Email: TechSupport@MicroCare.sg

ISO 9001:2015 Registered

© 2021 MicroCare, LLC. All Rights Reserved. "MicroCare", the MicroCare logo, and "Making Your Devices Better" are trademarks or registered trademarks of MicroCare, LLC. The information set forth herein is based on data believed to be reliable. MicroCare makes no warranties express or implied as to its accuracy and assumes no liability arising out of its use by others. This publication is not to be taken as a license to operate under, nor infringe upon, any patents not herein expressly described.